

Platinum curing agent for molding (TN/AB-XXPS series)

Application >>

- Low temperature vulcanization, tasteless products

Characteristic >>

- Tasteless low temperature vulcanization speed, stability, good mould release.



Specification Data Sheet >>

ITEM	Demand		
	TNA/B-25PS	TNA/B-45PS	TNA/B-65PS
Appearance	Black solid, no obvious mechanical impurities		
Hardness(Shore A)	10-30	40-50	60-80
A Usage(%)	0.5	0.5	0.5
B Usage	1.1-1.3	1.4-1.6	1.8-2.0
TS2(125°C*3MINS)	20-30	20-30	20-30
TC90(125°C*3MINS)	55-70	55-70	55-70
Mixed placement life (25°C environment ≥day)	3	3	3

Application

